

ALKALI-SILICA POTENTIAL REACTIVITY RATING LIST
April 30, 2010

This list supersedes the February 5, 2010 list. Note: Changes are not high-lighted on this list.

The following values are based on Illinois Modified ASTM C 1260 test results.

Please Note: Each coarse aggregate limestone or dolomite shall have an assigned expansion value of 0.05% and each fine aggregate limestone or dolomite (manufactured stone sand) shall have an assigned expansion value of 0.03%, unless otherwise noted below.

Dist.	Producer Name	Location	P/S No.	Ledge Description	Material Code	ASR Rating*	Testing** Frequency	Number of Tests	C 1293 Test***
91	AGGREGATE INDUSTRIES	EDWARDSBURG, MI	52600-07	ABOVE WATER	021CA11	A	1	1	
91	AGGREGATE INDUSTRIES	EDWARDSBURG, MI	52600-07	ABOVE & BELOW WATER	027FA02	B	2	3	
91	AGGREGATE INDUSTRIES	EDWARDSBURG, MI	52600-07	BELOW WATER	027FA02	B	2	6	
91	AGGREGATE INDUSTRIES	EDWARDSBURG, MI	52600-07	ABOVE WATER	027FA02	B	2	9	
91	AMERICAN AGGREGATE	NILES, MI	52600-08	BELOW WATER	027FA02	B	1	2	
91	AMERICAN AGGREGATE	NILES, MI	52600-08	ABOVE WATER	027FA02	B	2	7	
91	BAKLEY CONST. CORP.	HUNTLEY, IL	51110-28	ABOVE & BELOW WATER	020CA16	A	2	4	
91	BAKLEY CONST. CORP.	HUNTLEY, IL	51110-28	ABOVE & BELOW WATER	027FA02	A	2	3	
91	BAKLEY CONST. CORP.	HUNTLEY, IL	51110-28	ABOVE & BELOW WATER	020CA11	A	2	4	
91	BASS LAKE S & G	KNOX, IN	52100-76	ABOVE WATER	027FA01	B	1	1	
91	BEVERLY MATL'S, INC	ELGIN, IL	50890-22	ABOVE WATER	020CA11	A	2	4	
91	BEVERLY MATL'S, INC	ELGIN, IL	50890-22	BELOW WATER	020CA16	A	2	3	
91	BEVERLY MATL'S, INC	ELGIN, IL	50890-22	BELOW WATER	021CA11	A	2	3	
91	BEVERLY MATL'S, INC	ELGIN, IL	50890-22	ABOVE WATER	020CA16	A	2	4	
91	BEVERLY MATL'S, INC	ELGIN, IL	50890-22	ABOVE WATER	021CA16	A	2	4	
91	BEVERLY MATL'S, INC	ELGIN, IL	50890-22	BELOW WATER	021CA16	A	2	4	
91	BEVERLY MATL'S, INC	ELGIN, IL	50890-22	ABOVE WATER	021CA11	A	2	4	

* ASR Rating - Indicates ASR Expansion Value Range; A = < 0.16, B = 0.17 - 0.27, C = > 0.28; Please contact individual sources for ASR Expansion Value, when needed

** Testing Frequency: 1's, sample as needed until 3 tests are completed; 2's, sample in 2011; 3's, sample in 2010; Note: only 1 sample required per year indicated

***Where applicable, ASTM C 1293 results used; Replace ASTM C 1260 results with 0.08; Resample required during year indicated

ALKALI-SILICA POTENTIAL REACTIVITY RATING LIST
April 30, 2010

This list supersedes the February 5, 2010 list. Note: Changes are not high-lighted on this list.

The following values are based on Illinois Modified ASTM C 1260 test results.

Please Note: Each coarse aggregate limestone or dolomite shall have an assigned expansion value of 0.05% and each fine aggregate limestone or dolomite (manufactured stone sand) shall have an assigned expansion value of 0.03%, unless otherwise noted below.

Dist.	Producer Name	Location	P/S No.	Ledge Description	Material Code	ASR Rating*	Testing** Frequency	Number of Tests	C 1293 Test***
91	BEVERLY MATL'S, INC	ELGIN, IL	50890-22	BELOW WATER	020CA11	A	2	3	
91	BEVERLY MATL'S, INC	ELGIN, IL	50890-22	ABOVE WATER	027FA02	A	2	4	
91	BEVERLY MATL'S, INC	ELGIN, IL	50890-22	BELOW WATER	027FA02	A	2	3	
91	BEVERLY MATL'S, INC	HUNTLEY, IL	51110-41	ABOVE & BELOW WATER	027FA02	B	2	5	
91	BEVERLY MATL'S, INC	HUNTLEY, IL	51110-41	ABOVE & BELOW WATER	021CA11	A	2	4	
91	BEVERLY MATL'S, INC	HUNTLEY, IL	51110-41	ABOVE & BELOW WATER	020CA16	A	2	4	
91	BEVERLY MATL'S, INC	HUNTLEY, IL	51110-41	BELOW WATER	027FA02	B	1	1	
91	BEVERLY MATL'S, INC	HUNTLEY, IL	51110-41	ABOVE & BELOW WATER	020CA11	A	2	4	
91	BEVERLY MATL'S, INC	HUNTLEY, IL	51110-41	ABOVE WATER	027FA02	B	1	2	
91	BLUFF CITY MATERIALS	BARTLETT, IL	50310-09	ABOVE WATER	027FA02	B	2	5	
91	BLUFF CITY MATERIALS	BARTLETT, IL	50310-09	BELOW WATER	027FA02	B	2	5	
91	BLUFF CITY MATERIALS	BARTLETT, IL	50310-09	ABOVE & BELOW WATER	020CA11	A	2	6	
91	BLUFF CITY MATERIALS	BARTLETT, IL	50310-09	ABOVE & BELOW WATER	020CA16	A	2	5	
91	BLUFF CITY MATERIALS	BARTLETT, IL	50310-09	ABOVE & BELOW WATER	027FA02	B	2	4	
91	BLUFF CITY MATERIALS	BARTLETT, IL	50310-09	ABOVE WATER	020CA11	A	2	4	
91	BLUFF CITY MATERIALS	BARTLETT, IL	50310-09	ABOVE WATER	020CA16	A	2	4	
91	BLUFF CITY MATERIALS	ELGIN, IL	50890-08	ABOVE & BELOW WATER	027FA02	B	3	3	

* **ASR Rating** - Indicates ASR Expansion Value Range; A = < 0.16, B = 0.17 - 0.27, C = > 0.28; Please contact individual sources for ASR Expansion Value, when needed

** **Testing Frequency**: 1's, sample as needed until 3 tests are completed; 2's, sample in 2011; 3's, sample in 2010; Note: only 1 sample required per year indicated

***Where applicable, ASTM C 1293 results used; Replace ASTM C 1260 results with 0.08; Resample required during year indicated

ALKALI-SILICA POTENTIAL REACTIVITY RATING LIST
April 30, 2010

This list supersedes the February 5, 2010 list. Note: Changes are not high-lighted on this list.

The following values are based on Illinois Modified ASTM C 1260 test results.

Please Note: Each coarse aggregate limestone or dolomite shall have an assigned expansion value of 0.05% and each fine aggregate limestone or dolomite (manufactured stone sand) shall have an assigned expansion value of 0.03%, unless otherwise noted below.

Dist.	Producer Name	Location	P/S No.	Ledge Description	Material Code	ASR Rating*	Testing** Frequency	Number of Tests	C 1293 Test***
91	BLUFF CITY MATERIALS	ELGIN, IL	50890-08	BELOW WATER	027FA02	B	1	1	
91	BLUFF CITY MATERIALS	ELGIN, IL	50890-08	ABOVE & BELOW WATER	020CA11	A	3	3	
91	BLUFF CITY MATERIALS	ELGIN, IL	50890-08	ABOVE & BELOW WATER	020CA16	A	3	3	
91	CARPENTERSVILLE Q.	CARPENTERSVILLE, IL	50890-10	BELOW WATER	020CA16	B	1	1	
91	CARPENTERSVILLE Q.	CARPENTERSVILLE, IL	50890-10	BELOW WATER	027FA02	B	2	4	
91	CARPENTERSVILLE Q.	CARPENTERSVILLE, IL	50890-10	BELOW WATER	027FA01	B	1	1	
91	CEDAR LAKE S. & G.	HARTFORD, WI	52400-39	ABOVE WATER	020CA11	A	2	4	
91	CEDAR LAKE S. & G.	HARTFORD, WI	52400-39	ABOVE WATER	020CA16	B	2	4	
91	CEDAR LAKE S. & G.	HARTFORD, WI	52400-39	ABOVE WATER	027FA02	B	2	4	
91	CORAL LAKE S & G	MARENGO, IL	51110-46	ABOVE & BELOW WATER	027FA02	B	2	4	
91	CORAL LAKE S & G	MARENGO, IL	51110-46	ABOVE & BELOW WATER	020CA07	A	2	4	
91	CRETEX MATERIAL, INC	BURLINGTON, WI	52400-36	ABOVE WATER	027FA02	B	2	6	
91	CRETEX MATERIAL, INC	BURLINGTON, WI	52400-36	ABOVE WATER	020CA11	A	2	6	
91	CRETEX MATERIAL, INC	BURLINGTON, WI	52400-36	ABOVE WATER	020CA16	A	2	3	
91	ELKHART CO. GRAVEL	MIDDLEBURY, IN	52100-56	ABOVE WATER	027FA02	B	1	2	
91	ELKHART CO. GRAVEL	NEW PARIS, IN	52100-59	BELOW WATER	027FA02	C	1	1	
91	ELKHART CO. GRAVEL	NEW PARIS, IN	52100-59	ABOVE WATER	027FA02	B	1	2	

* **ASR Rating** - Indicates ASR Expansion Value Range; A = < 0.16, B = 0.17 - 0.27, C = > 0.28; Please contact individual sources for ASR Expansion Value, when needed

** **Testing Frequency**: 1's, sample as needed until 3 tests are completed; 2's, sample in 2011; 3's, sample in 2010; Note: only 1 sample required per year indicated

***Where applicable, ASTM C 1293 results used; Replace ASTM C 1260 results with 0.08; Resample required during year indicated

ALKALI-SILICA POTENTIAL REACTIVITY RATING LIST
April 30, 2010

This list supersedes the February 5, 2010 list. Note: Changes are not high-lighted on this list.

The following values are based on Illinois Modified ASTM C 1260 test results.

Please Note: Each coarse aggregate limestone or dolomite shall have an assigned expansion value of 0.05% and each fine aggregate limestone or dolomite (manufactured stone sand) shall have an assigned expansion value of 0.03%, unless otherwise noted below.

Dist.	Producer Name	Location	P/S No.	Ledge Description	Material Code	ASR Rating*	Testing** Frequency	Number of Tests	C 1293 Test***
91	ELKHART CO. GRAVEL	NEW PARIS, IN	52100-59	ABOVE & BELOW WATER	027FA02	B	1	1	
91	ELMHURST CHICAGO ST.	KANEVILLE, IL	50890-29	ABOVE WATER	027FA02	B	2	4	
91	ELMHURST CHICAGO ST.	KANEVILLE, IL	50890-29	BELOW WATER	027FA02	A	3	5	
91	ELMHURST CHICAGO ST.	KANEVILLE, IL	50890-29	BELOW WATER	020CA16	A	2	5	
91	ELMHURST CHICAGO ST.	KANEVILLE, IL	50890-29	BELOW WATER	020CA14	A	1	1	
91	ELMHURST CHICAGO ST.	ROMEOVILLE, IL	51970-05	ABOVE WATER	027FA01	A	1	1	
91	HIGH GRADE MATERIALS	PLAINWELL, MI	52600-09	ABOVE WATER	027FA02	B	2	3	
91	LAFARGE ELBURN	ELBURN, IL	50890-27	ABOVE & BELOW WATER	020CA11	A	2	5	
91	LAFARGE ELBURN	ELBURN, IL	50890-27	ABOVE & BELOW WATER	020CA16	A	2	6	
91	LAFARGE ELBURN	ELBURN, IL	50890-27	ABOVE & BELOW WATER	027FA02	B	2	4	
91	LILY POND STONE, LLC	WOODSTOCK, IL	51110-62	ABOVE WATER	020CA16	A	3	4	
91	LILY POND STONE, LLC	WOODSTOCK, IL	51110-62	ABOVE WATER	021CA16	A	1	1	
91	LILY POND STONE, LLC	WOODSTOCK, IL	51110-62	ABOVE WATER	020CA11	A	3	4	
91	LILY POND STONE, LLC	WOODSTOCK, IL	51110-62	ABOVE WATER	021CA11	A	3	5	
91	LILY POND STONE, LLC	WOODSTOCK, IL	51110-62	ABOVE WATER	027FA02	B	3	4	
91	MATERIAL SERVICE	ALGONQUIN, IL	51110-12	ABOVE & BELOW WATER	027FA02	B	2	6	
91	MATERIAL SERVICE	ALGONQUIN, IL	51110-12	ABOVE & BELOW WATER	020CA16	A	2	5	

* ASR Rating - Indicates ASR Expansion Value Range; A = < 0.16, B = 0.17 - 0.27, C = > 0.28; Please contact individual sources for ASR Expansion Value, when needed

** Testing Frequency: 1's, sample as needed until 3 tests are completed; 2's, sample in 2011; 3's, sample in 2010; Note: only 1 sample required per year indicated

***Where applicable, ASTM C 1293 results used; Replace ASTM C 1260 results with 0.08; Resample required during year indicated

ALKALI-SILICA POTENTIAL REACTIVITY RATING LIST **April 30, 2010**

This list supersedes the February 5, 2010 list. Note: Changes are not high-lighted on this list.

The following values are based on Illinois Modified ASTM C 1260 test results.

Please Note: Each coarse aggregate limestone or dolomite shall have an assigned expansion value of 0.05% and each fine aggregate limestone or dolomite (manufactured stone sand) shall have an assigned expansion value of 0.03%, unless otherwise noted below.

Dist.	Producer Name	Location	P/S No.	Ledge Description	Material Code	ASR Rating*	Testing** Frequency	Number of Tests	C 1293 Test***
91	MATERIAL SERVICE	ALGONQUIN, IL	51110-12	ABOVE & BELOW WATER	027FA01	B	1	2	
91	MATERIAL SERVICE	ALGONQUIN, IL	51110-12	ABOVE & BELOW WATER	020CA11	B	2	5	
91	MATERIAL SERVICE	ROMEOVILLE, IL	51972-02	FM20 BLEND SAND -0.0-41.1M	029FA20	A	1	2	
91	MEYER MATERIAL CO.	ALGONQUIN, IL	51110-07	ABOVE & BELOW WATER	021CA11	A	2	5	
91	MEYER MATERIAL CO.	ALGONQUIN, IL	51110-07	ABOVE & BELOW WATER	021CA16	A	2	4	
91	MEYER MATERIAL CO.	ALGONQUIN, IL	51110-07	ABOVE & BELOW WATER	027FA02	B	2	5	2011
91	MEYER MATERIAL CO.	ALGONQUIN, IL	51110-07	ABOVE & BELOW WATER	020CA16	A	2	4	
91	MEYER MATERIAL CO.	ALGONQUIN, IL	51110-07	ABOVE & BELOW WATER	020CA11	A	2	5	
91	MEYER MATERIAL CO.	ALGONQUIN, IL	51110-42	ABOVE & BELOW WATER	021CA16	A	3	4	
91	MEYER MATERIAL CO.	ALGONQUIN, IL	51110-42	ABOVE & BELOW WATER	020CA16	A	2	4	
91	MEYER MATERIAL CO.	ALGONQUIN, IL	51110-42	ABOVE & BELOW WATER	027FA02	B	3	3	
91	MEYER MATERIAL CO.	ALGONQUIN, IL	51110-42	ABOVE & BELOW WATER	020CA11	A	2	4	
91	MEYER MATERIAL CO.	HARVARD, IL	51110-45	ABOVE & BELOW WATER	020CA11	A	3	3	
91	MEYER MATERIAL CO.	HARVARD, IL	51110-45	BELOW WATER	027FA02	B	3	3	
91	MEYER MATERIAL CO.	HARVARD, IL	51110-45	ABOVE & BELOW WATER	027FA02	B	3	3	
91	MEYER MATERIAL CO.	HARVARD, IL	51110-45	ABOVE & BELOW WATER	020CA16	A	3	3	
91	MEYER MATERIAL CO.	MARENGO, IL	51110-03	ABOVE & BELOW WATER	021CA16	A	2	4	

* **ASR Rating** - Indicates ASR Expansion Value Range; A = < 0.16, B = 0.17 - 0.27, C = > 0.28; Please contact individual sources for ASR Expansion Value, when needed

** **Testing Frequency**: 1's, sample as needed until 3 tests are completed; 2's, sample in 2011; 3's, sample in 2010; Note: only 1 sample required per year indicated

***Where applicable, ASTM C 1293 results used; Replace ASTM C 1260 results with 0.08; Resample required during year indicated

ALKALI-SILICA POTENTIAL REACTIVITY RATING LIST **April 30, 2010**

This list supersedes the February 5, 2010 list. Note: Changes are not high-lighted on this list.

The following values are based on Illinois Modified ASTM C 1260 test results.

Please Note: Each coarse aggregate limestone or dolomite shall have an assigned expansion value of 0.05% and each fine aggregate limestone or dolomite (manufactured stone sand) shall have an assigned expansion value of 0.03%, unless otherwise noted below.

Dist.	Producer Name	Location	P/S No.	Ledge Description	Material Code	ASR Rating*	Testing** Frequency	Number of Tests	C 1293 Test***
91	MEYER MATERIAL CO.	MARENGO, IL	51110-03	ABOVE & BELOW WATER	027FA02	B	2	4	
91	MEYER MATERIAL CO.	MARENGO, IL	51110-03	ABOVE & BELOW WATER	020CA11	A	2	4	
91	MEYER MATERIAL CO.	MCHENRY, IL	51110-11	ABOVE WATER	021CA16	A	2	4	
91	MEYER MATERIAL CO.	MCHENRY, IL	51110-11	ABOVE WATER	020CA11	B	2	4	
91	MEYER MATERIAL CO.	MCHENRY, IL	51110-11	ABOVE WATER	021CA11	A	2	4	
91	MEYER MATERIAL CO.	MCHENRY, IL	51110-11	ABOVE WATER	020CA16	B	2	4	
91	MEYER MATERIAL CO.	MCHENRY, IL	51110-11	ABOVE WATER	027FA02	B	2	5	
91	MEYER MATERIAL CO.	TWIN LAKES, WI	52400-44	ABOVE WATER	027FA02	B	2	4	
91	MEYER MATERIAL CO.	TWIN LAKES, WI	52400-44	ABOVE WATER	020CA11	A	2	4	
91	MEYER MATERIAL CO.	TWIN LAKES, WI	52400-44	ABOVE WATER	020CA16	A	2	4	
91	MIDWEST AGGREGATES	ANTIOCH, IL	50970-20	ABOVE & BELOW WATER	020CA11	A	2	4	
91	MIDWEST AGGREGATES	ANTIOCH, IL	50970-20	ABOVE & BELOW WATER	020CA16	A	2	4	
91	MIDWEST AGGREGATES	ANTIOCH, IL	50970-20	ABOVE & BELOW WATER	027FA02	B	2	5	
91	MOOSE LAKE AGG.	NILES, MI	52600-06	ABOVE & BELOW WATER	027FA02	B	1	1	
91	MOOSE LAKE AGG.	NILES, MI	52600-06	BELOW WATER	027FA02	B	1	1	
91	MOOSE LAKE AGG.	NILES, MI	52600-06	ABOVE WATER	027FA02	B	2	6	
91	NORTHERN MATERIALS	HUNTLEY, IL	51110-32	BELOW WATER	027FA02	B	3	7	

* **ASR Rating** - Indicates ASR Expansion Value Range; A = < 0.16, B = 0.17 - 0.27, C = > 0.28; Please contact individual sources for ASR Expansion Value, when needed

** **Testing Frequency**: 1's, sample as needed until 3 tests are completed; 2's, sample in 2011; 3's, sample in 2010; Note: only 1 sample required per year indicated

***Where applicable, ASTM C 1293 results used; Replace ASTM C 1260 results with 0.08; Resample required during year indicated

ALKALI-SILICA POTENTIAL REACTIVITY RATING LIST
April 30, 2010

This list supersedes the February 5, 2010 list. Note: Changes are not high-lighted on this list.

The following values are based on Illinois Modified ASTM C 1260 test results.

Please Note: Each coarse aggregate limestone or dolomite shall have an assigned expansion value of 0.05% and each fine aggregate limestone or dolomite (manufactured stone sand) shall have an assigned expansion value of 0.03%, unless otherwise noted below.

Dist.	Producer Name	Location	P/S No.	Ledge Description	Material Code	ASR Rating*	Testing** Frequency	Number of Tests	C 1293 Test***
91	NORTHERN MATERIALS	HUNTLEY, IL	51110-32	BELOW WATER	020CA07	B	1	1	
91	PRAIRIE MATERIAL	KANEVILLE, IL	50890-37	BELOW WATER	020CA11	A	3	3	
91	PRAIRIE MATERIAL	KANEVILLE, IL	50890-37	ABOVE & BELOW WATER	027FA02	A	1	1	
91	PRAIRIE MATERIAL	KANEVILLE, IL	50890-37	BELOW WATER	027FA02	B	3	3	
91	PRAIRIE MATERIAL	MARENGO, IL	51110-39	ABOVE & BELOW WATER	020CA16	A	2	4	
91	PRAIRIE MATERIAL	MARENGO, IL	51110-39	ABOVE & BELOW WATER	020CA11	A	2	4	
91	PRAIRIE MATERIAL	MARENGO, IL	51110-39	ABOVE & BELOW WATER	027FA02	B	2	4	
91	RELIABLE S. & G.	ISLAND LAKE, IL	51110-30	ABOVE & BELOW WATER	027FA02	B	3	3	
91	RIETH-RILEY CONST CO	ROLLING PRAIRE, IN	52100-58	ABOVE WATER	027FA02	B	1	1	
91	ROCK ROAD NELSON LLC	EAST TROY, WI	52400-50	ABOVE WATER	027FA02	B	2	4	
91	ROCK ROAD NELSON LLC	EAST TROY, WI	52400-50	ABOVE WATER	020CA16	B	2	4	
91	ROCK ROAD NELSON LLC	EAST TROY, WI	52400-50	ABOVE WATER	020CA11	A	3	5	
91	ROCK ROAD NELSON LLC	EAST TROY, WI	52400-50	ABOVE WATER	027FA01	B	1	1	
91	ROCK ROAD NELSON LLC	WHITEWATER, WI	52400-48	ABOVE WATER	027FA02	B	3	4	
91	ROCK ROAD NELSON LLC	WHITEWATER, WI	52400-48	ABOVE WATER	020CA11	A	3	4	
91	ROCK ROAD NELSON LLC	WHITEWATER, WI	52400-48	ABOVE WATER	020CA16	A	3	4	
91	ROCKY MOUNTAIN ENT.	ATHENS, WI	52402-14	LEVEL ONE	022CA13	A	1	1	

* **ASR Rating** - Indicates ASR Expansion Value Range; A = < 0.16, B = 0.17 - 0.27, C = > 0.28; Please contact individual sources for ASR Expansion Value, when needed

** **Testing Frequency**: 1's, sample as needed until 3 tests are completed; 2's, sample in 2011; 3's, sample in 2010; Note: only 1 sample required per year indicated

***Where applicable, ASTM C 1293 results used; Replace ASTM C 1260 results with 0.08; Resample required during year indicated

ALKALI-SILICA POTENTIAL REACTIVITY RATING LIST
April 30, 2010

This list supersedes the February 5, 2010 list. Note: Changes are not high-lighted on this list.

The following values are based on Illinois Modified ASTM C 1260 test results.

Please Note: Each coarse aggregate limestone or dolomite shall have an assigned expansion value of 0.05% and each fine aggregate limestone or dolomite (manufactured stone sand) shall have an assigned expansion value of 0.03%, unless otherwise noted below.

Dist.	Producer Name	Location	P/S No.	Ledge Description	Material Code	ASR Rating*	Testing** Frequency	Number of Tests	C 1293 Test***
91	SPRUCE LAKE S & G	RICHMOND, IL	51110-64	ABOVE WATER	020CA11	A	2	3	
91	SPRUCE LAKE S & G	RICHMOND, IL	51110-64	ABOVE WATER	027FA02	B	2	3	
91	THELEN SAND & GRAVEL	ANTIOCH, IL	50970-01	ABOVE WATER	027FA02	B	2	3	
91	THELEN SAND & GRAVEL	ANTIOCH, IL	50970-01	BELOW WATER	027FA02	B	3	4	
91	THELEN SAND & GRAVEL	ANTIOCH, IL	50970-01	BELOW WATER	020CA11	B	3	4	
91	THELEN SAND & GRAVEL	ANTIOCH, IL	50970-01	ABOVE WATER	021CA11	A	3	4	
91	THELEN SAND & GRAVEL	ANTIOCH, IL	50970-01	ABOVE WATER	020CA11	A	3	3	
91	THELEN SAND & GRAVEL	ANTIOCH, IL	50970-01	BELOW WATER	021CA11	B	3	4	
91	THELEN SAND & GRAVEL	ANTIOCH, IL	50970-02	ABOVE & BELOW WATER	020CA16	A	2	4	
91	THELEN SAND & GRAVEL	ANTIOCH, IL	50970-02	ABOVE & BELOW WATER	027FA02	B	3	5	
91	THELEN SAND & GRAVEL	ANTIOCH, IL	50970-02	ABOVE & BELOW WATER	020CA11	B	2	4	
91	THELEN SAND & GRAVEL	ANTIOCH, IL	50970-02	ABOVE & BELOW WATER	021CA11	A	2	4	
91	THELEN SAND & GRAVEL	HEBRON, WI	52400-27	ABOVE & BELOW WATER	020CA16	A	2	4	
91	THELEN SAND & GRAVEL	HEBRON, WI	52400-27	ABOVE & BELOW WATER	027FA02	B	2	5	
91	THELEN SAND & GRAVEL	HEBRON, WI	52400-27	ABOVE & BELOW WATER	020CA11	A	2	5	
91	VULCAN MATERIALS	JOLIET, IL	51972-19	0.0-27.4M	022CA11	A	1	1	
91	VULCAN MATERIALS	MCCOOK, IL	50312-78	VARIOUS	028FA02	A	1	2	

* **ASR Rating** - Indicates ASR Expansion Value Range; A = < 0.16, B = 0.17 - 0.27, C = > 0.28; Please contact individual sources for ASR Expansion Value, when needed

** **Testing Frequency**: 1's, sample as needed until 3 tests are completed; 2's, sample in 2011; 3's, sample in 2010; Note: only 1 sample required per year indicated

***Where applicable, ASTM C 1293 results used; Replace ASTM C 1260 results with 0.08; Resample required during year indicated

ALKALI-SILICA POTENTIAL REACTIVITY RATING LIST **April 30, 2010**

This list supersedes the February 5, 2010 list. Note: Changes are not high-lighted on this list.

The following values are based on Illinois Modified ASTM C 1260 test results.

Please Note: Each coarse aggregate limestone or dolomite shall have an assigned expansion value of 0.05% and each fine aggregate limestone or dolomite (manufactured stone sand) shall have an assigned expansion value of 0.03%, unless otherwise noted below.

Dist.	Producer Name	Location	P/S No.	Ledge Description	Material Code	ASR Rating*	Testing** Frequency	Number of Tests	C 1293 Test***
91	VULCAN MATERIALS	RACINE, WI	52402-01	68.3-79.2M	028FA20	A	1	1	
91	VULCAN MATERIALS	SUSSEX, WI	52402-64	0.0-20.4M	028FA20	A	1	1	
91	WELCH BROS., INC.	HAMPSHIRE, IL	50890-53	BELOW WATER	027FA02	B	2	4	
91	WELCH BROS., INC.	HAMPSHIRE, IL	50890-53	BELOW WATER	020CA11	A	2	6	
91	WELCH BROS., INC.	HAMPSHIRE, IL	50890-53	BELOW WATER	020CA16	A	2	5	
92	ACME FUEL & MATLS.	MUSCATINE, IA	52200-12	BELOW WATER	027FA01	B	2	3	
92	ADELINE S & G	ADELINE, IL	51410-96	ABOVE WATER	021CA16	A	3	3	
92	ADELINE S & G	ADELINE, IL	51410-96	ABOVE WATER	027FA01	B	3	3	
92	AGGREGATE MATERIALS	DUBUQUE, IA	52200-29	BELOW WATER	027FA01	C	3	3	
92	ALLIANCE MATERIALS	DIXON, IL	51030-51	BELOW WATER	027FA01	B	3	3	
92	ALLIANCE MATERIALS	GALT, IL	51950-89	ABOVE & BELOW WATER	027FA01	B	3	3	
92	BLUFF CITY MATERIALS	SOUTH BELOIT, IL	52010-20	ABOVE WATER	029FA02	B	1	2	
92	BLUFF CITY MATERIALS	SOUTH BELOIT, IL	52010-20	ABOVE & BELOW WATER	029FA02	A	3	3	
92	BLUFF CITY MATERIALS	SOUTH BELOIT, IL	52010-20	ABOVE WATER	021CA16	B	1	1	
92	BLUFF CITY MATERIALS	SOUTH BELOIT, IL	52010-20	ABOVE & BELOW WATER	021CA16	A	1	1	
92	BUILDERS SAND&CEMENT	ALBANY, IL	51610-33	BELOW WATER	027FA01	C	3	3	
92	C. J. MATERIALS	LYNDON, IL	51950-84	ABOVE WATER	027FA01	B	3	3	

* **ASR Rating** - Indicates ASR Expansion Value Range; A = < 0.16, B = 0.17 - 0.27, C = > 0.28; Please contact individual sources for ASR Expansion Value, when needed

** **Testing Frequency**: 1's, sample as needed until 3 tests are completed; 2's, sample in 2011; 3's, sample in 2010; Note: only 1 sample required per year indicated

***Where applicable, ASTM C 1293 results used; Replace ASTM C 1260 results with 0.08; Resample required during year indicated

ALKALI-SILICA POTENTIAL REACTIVITY RATING LIST **April 30, 2010**

This list supersedes the February 5, 2010 list. Note: Changes are not high-lighted on this list.

The following values are based on Illinois Modified ASTM C 1260 test results.

Please Note: Each coarse aggregate limestone or dolomite shall have an assigned expansion value of 0.05% and each fine aggregate limestone or dolomite (manufactured stone sand) shall have an assigned expansion value of 0.03%, unless otherwise noted below.

Dist.	Producer Name	Location	P/S No.	Ledge Description	Material Code	ASR Rating*	Testing** Frequency	Number of Tests	C 1293 Test***
92	CONMAT, INC.	FORRESTON, IL	51410-02	ABOVE WATER	027FA01	B	1	2	
92	CONMAT, INC.	FORRESTON, IL	51410-02	ABOVE WATER	029FA01	A	1	1	
92	FISCHER EXCAVATING	FORRESTON, IL	51410-04	ABOVE WATER	027FA01	B	3	3	
92	HAHN READY MIX INC.	MUSCATINE, IA	52200-43	BELOW WATER	027FA01	C	1	2	
92	JANESVILLE SAND & GR	JANESVILLE, WI	52400-01	0.0-24.4M ABOVE WATER	027FA02	B	1	1	
92	JANESVILLE SAND & GR	JANESVILLE, WI	52400-01	0.0-24.4M ABOVE WATER	027FA01	B	1	1	
92	KENNEDY, W.J. & SONS	BELOIT, WI	52400-26	ABOVE WATER	027FA01	B	3	3	
92	LEE, CHARLES & SON	IRENE, IL	50070-12	ABOVE WATER	021CA16	A	1	1	
92	LEE, CHARLES & SON	IRENE, IL	50070-12	ABOVE WATER	027FA01	A	1	2	
92	MACKLIN INCORPORATED	SHABBONA, IL	51030-85	ABOVE WATER	027FA01	B	1	1	
92	MANN BROS., INC.	BELOIT, WI	52400-49	ABOVE WATER	027FA02	B	3	3	
92	MANN BROS., INC.	BELOIT, WI	52400-49	ABOVE WATER	020CA16	A	2	4	
92	MEYER MATERIAL CO.	BELVIDERE, IL	50070-01	BELOW WATER	027FA01	C	3	3	
92	QUALITY CONCRETE CO.	SAVANNA, IL	50150-90	BELOW WATER	027FA01	C	3	3	
92	RIVERSTONE GROUP INC	CORDOVA, IL	51610-37	ABOVE & BELOW WATER	027FA01	C	2	3	
92	RIVERSTONE GROUP,INC	ALBANY, IL	51610-24	BELOW WATER	027FA01	C	2	5	
92	RIVERSTONE GROUP,INC	CORDOVA, IL	51610-34	BELOW WATER	027FA01	C	1	1	

* ASR Rating - Indicates ASR Expansion Value Range; A = < 0.16, B = 0.17 - 0.27, C = > 0.28; Please contact individual sources for ASR Expansion Value, when needed

** Testing Frequency: 1's, sample as needed until 3 tests are completed; 2's, sample in 2011; 3's, sample in 2010; Note: only 1 sample required per year indicated

***Where applicable, ASTM C 1293 results used; Replace ASTM C 1260 results with 0.08; Resample required during year indicated

ALKALI-SILICA POTENTIAL REACTIVITY RATING LIST
April 30, 2010

This list supersedes the February 5, 2010 list. Note: Changes are not high-lighted on this list.

The following values are based on Illinois Modified ASTM C 1260 test results.

Please Note: Each coarse aggregate limestone or dolomite shall have an assigned expansion value of 0.05% and each fine aggregate limestone or dolomite (manufactured stone sand) shall have an assigned expansion value of 0.03%, unless otherwise noted below.

Dist.	Producer Name	Location	P/S No.	Ledge Description	Material Code	ASR Rating*	Testing** Frequency	Number of Tests	C 1293 Test***
92	RIVERSTONE GROUP, INC	MC CAUSLAND, IA	52200-35	BELOW WATER	027FA01	C	1	1	
92	ROCK RIVER READY MIX	ROCK FALLS, IL	51950-82	ABOVE & BELOW WATER	027FA01	B	2	3	
92	ROGERS R-M & MATLS	ROSCOE, IL	52010-92	ABOVE WATER	027FA01	A	3	4	
92	ROGERS R-M & MATLS.	BYRON, IL	51410-22	ABOVE WATER	027FA01	B	2	4	
92	ROSCOE ROCK & SAND	ROSCOE, IL	52010-90	ABOVE WATER	027FA01	B	1	1	
92	SPRUCE LAKE S. & G.	BELVIDERE, IL	50070-13	ABOVE & BELOW WATER	020CA16	A	1	1	
92	SPRUCE LAKE S. & G.	BELVIDERE, IL	50070-13	ABOVE WATER	020CA11	A	2	3	
92	SPRUCE LAKE S. & G.	BELVIDERE, IL	50070-13	ABOVE & BELOW WATER	027FA02	B	3	3	
92	SPRUCE LAKE S. & G.	BELVIDERE, IL	50070-13	ABOVE WATER	027FA02	B	1	1	
92	SPRUCE LAKE S. & G.	BELVIDERE, IL	50070-13	ABOVE WATER	020CA16	A	2	3	
92	SPRUCE LAKE S. & G.	BELVIDERE, IL	50070-13	BELOW WATER	027FA02	B	1	1	
92	WENDLING QUARRIES	CAMANACHE, IA	52200-40	BELOW WATER	027FA01	C	2	4	
92	WENDLING QUARRIES	FOLLETTTS, IA	52200-45	BELOW WATER	027FA01	C	3	3	
92	WENDLING QUARRIES	MOSCOW, IA	52200-44	BELOW WATER	027FA01	C	2	4	
92	WENDLING QUARRIES	SABULA, IA	52200-33	BELOW WATER	027FA01	C	1	2	
92	WENDLING QUARRIES	SABULA, IA	52200-33	ABOVE & BELOW WATER	027FA01	C	3	3	
92	WILLIAM CHARLES CONS	BELVIDERE, IL	50072-01	12.2-26.5M	022CA11	A	1	1	

* **ASR Rating** - Indicates ASR Expansion Value Range; A = < 0.16, B = 0.17 - 0.27, C = > 0.28; Please contact individual sources for ASR Expansion Value, when needed

** **Testing Frequency:** 1's, sample as needed until 3 tests are completed; 2's, sample in 2011; 3's, sample in 2010; Note: only 1 sample required per year indicated

***Where applicable, ASTM C 1293 results used; Replace ASTM C 1260 results with 0.08; Resample required during year indicated

ALKALI-SILICA POTENTIAL REACTIVITY RATING LIST **April 30, 2010**

This list supersedes the February 5, 2010 list. Note: Changes are not high-lighted on this list.

The following values are based on Illinois Modified ASTM C 1260 test results.

Please Note: Each coarse aggregate limestone or dolomite shall have an assigned expansion value of 0.05% and each fine aggregate limestone or dolomite (manufactured stone sand) shall have an assigned expansion value of 0.03%, unless otherwise noted below.

Dist.	Producer Name	Location	P/S No.	Ledge Description	Material Code	ASR Rating*	Testing** Frequency	Number of Tests	C 1293 Test***
92	WILLIAM CHARLES CONS	ROCKFORD, IL	52010-07	BELOW WATER	020CA16	A	1	1	
92	WILLIAM CHARLES CONS	ROCKFORD, IL	52010-07	BELOW WATER	020CA07	A	1	1	
92	WILLIAM CHARLES CONS	ROCKFORD, IL	52010-07	BELOW WATER	027FA01	B	2	7	
92	WILLIAM CHARLES CONS	ROSCOE, IL	52010-14	BELOW WATER	027FA01	B	3	3	
93	INDIAN VALLEY STONE	BUREAU JUNCTION, IL	50110-05	ABOVE WATER	027FA01	B	3	3	
93	IRVING MATERIALS	KEWANNA, IN	52100-77	BELOW WATER	027FA01	C	1	2	
93	KELLYCO, INC.	NORWAY, IL	50990-54	ABOVE & BELOW WATER	027FA01	B	1	1	
93	LAFARGE NA AUX SABLE	MORRIS, IL	50630-10	ABOVE & BELOW WATER	027FA02	B	1	1	
93	LAFARGE NA AUX SABLE	MORRIS, IL	50630-10	BELOW WATER	020CA16	A	1	2	
93	LAFARGE NA AUX SABLE	MORRIS, IL	50630-10	BELOW WATER	027FA02	B	2	4	
93	LAFARGE NA AUX SABLE	MORRIS, IL	50630-10	ABOVE & BELOW WATER	020CA16	A	1	1	
93	LAFARGE NA SHERIDAN	SHERIDAN, IL	50990-45	ABOVE WATER	027FA02	B	3	5	
93	LAFARGE NA SHERIDAN	SHERIDAN, IL	50990-45	ABOVE WATER	020CA16	A	2	4	
93	LAFARGE NA SHERIDAN	SHERIDAN, IL	50990-45	ABOVE WATER	027FA01	C	1	1	
93	MORRIS SAND & GRAVEL	MORRIS, IL	50630-09	BELOW WATER	027FA02	B	2	4	
93	PRAIRIE MATERIAL	PAXTON, IL	50530-02	BELOW WATER	027FA01	B	2	5	
93	SENECA S & G	SENECA, IL	50990-47	ABOVE & BELOW WATER	027FA01	B	3	4	

* **ASR Rating** - Indicates ASR Expansion Value Range; A = < 0.16, B = 0.17 - 0.27, C = > 0.28; Please contact individual sources for ASR Expansion Value, when needed

** **Testing Frequency**: 1's, sample as needed until 3 tests are completed; 2's, sample in 2011; 3's, sample in 2010; Note: only 1 sample required per year indicated

***Where applicable, ASTM C 1293 results used; Replace ASTM C 1260 results with 0.08; Resample required during year indicated

ALKALI-SILICA POTENTIAL REACTIVITY RATING LIST **April 30, 2010**

This list supersedes the February 5, 2010 list. Note: Changes are not high-lighted on this list.

The following values are based on Illinois Modified ASTM C 1260 test results.

Please Note: Each coarse aggregate limestone or dolomite shall have an assigned expansion value of 0.05% and each fine aggregate limestone or dolomite (manufactured stone sand) shall have an assigned expansion value of 0.03%, unless otherwise noted below.

Dist.	Producer Name	Location	P/S No.	Ledge Description	Material Code	ASR Rating*	Testing** Frequency	Number of Tests	C 1293 Test***
93	SENECA S & G	SENECA, IL	50990-47	ABOVE & BELOW WATER	027FA02	B	1	1	
93	TRICON	NORMANDY, IL	50110-12	ABOVE & BELOW WATER	027FA02	B	3	4	
93	TRICON	WALNUT, IL	50110-29	ABOVE & BELOW WATER	027FA02	B	1	2	
93	TRICON	WALNUT, IL	50110-29	BELOW WATER	027FA02	B	1	1	
93	TRICON	WALNUT, IL	50110-29	ABOVE WATER	027FA01	B	1	1	
93	U C PAVING, INC.	PERU, IL	50110-15	ABOVE & BELOW WATER	027FA01	B	2	3	
93	VALLEY VIEW INDUST.	FAIRBURY, IL	51052-15	3.5M FACE	022CA16	A	1	1	
93	VULCAN MATERIALS	CORTLAND, IL	50370-02	S & G ABOVE ROCK	027FA01	B	2	3	
93	VULCAN MATERIALS	CORTLAND, IL	50370-02	S & G ABOVE ROCK	020CA16	A	1	1	
93	WESTERN AGGREGATES	TROY GROVE, IL	50990-52	ABOVE WATER	027FA02	B	3	3	
94	CARRI SCHARF MATL CO	EAST PEORIA, IL	51790-38	ABOVE WATER	027FA01	B	3	4	
94	CARRI SCHARF MATL CO	EAST PEORIA, IL	51790-38	ABOVE & BELOW WATER	027FA01	B	1	1	
94	CARRI SCHARF MATL.	PEKIN, IL	51790-39	BELOW WATER	027FA01	B	1	2	
94	CONSTRUCTION MATLS.	SPRING BAY, IL	52030-23	BELOW WATER	027FA01	B	3	5	
94	CORNICK SAND & GRAVEL	PEKIN, IL	51790-15	BELOW WATER	027FA01	B	1	1	
94	CORNICK SAND & GRAVEL	PEKIN, IL	51790-15	ABOVE & BELOW WATER	020CA11	A	1	1	
94	CORNICK SAND & GRAVEL	PEKIN, IL	51790-15	ABOVE & BELOW WATER	027FA01	B	3	5	

* **ASR Rating** - Indicates ASR Expansion Value Range; A = < 0.16, B = 0.17 - 0.27, C = > 0.28; Please contact individual sources for ASR Expansion Value, when needed

** **Testing Frequency**: 1's, sample as needed until 3 tests are completed; 2's, sample in 2011; 3's, sample in 2010; Note: only 1 sample required per year indicated

***Where applicable, ASTM C 1293 results used; Replace ASTM C 1260 results with 0.08; Resample required during year indicated

ALKALI-SILICA POTENTIAL REACTIVITY RATING LIST **April 30, 2010**

This list supersedes the February 5, 2010 list. Note: Changes are not high-lighted on this list.

The following values are based on Illinois Modified ASTM C 1260 test results.

Please Note: Each coarse aggregate limestone or dolomite shall have an assigned expansion value of 0.05% and each fine aggregate limestone or dolomite (manufactured stone sand) shall have an assigned expansion value of 0.03%, unless otherwise noted below.

Dist.	Producer Name	Location	P/S No.	Ledge Description	Material Code	ASR Rating*	Testing** Frequency	Number of Tests	C 1293 Test***
94	CULLINAN, R.A. & SONS	E. PEORIA, IL	51790-34	BELOW WATER	027FA01	A	1	2	
94	CULLINAN, R.A. & SONS	E. PEORIA, IL	51790-34	ABOVE WATER	027FA01	A	1	2	
94	CULLINAN, R.A. & SONS	PEKIN, IL	51790-24	ABOVE WATER	027FA01	B	3	5	
94	DUCK CREEK S. & G.	BANNER, IL	50570-02	BELOW WATER	027FA01	B	3	4	
94	GALENA ROAD GRAVEL	CHILLICOTHE, IL	51430-19	ABOVE WATER	027FA01	B	3	5	
94	GALENA ROAD GRAVEL	CHILLICOTHE, IL	51430-19	BELOW WATER	027FA01	B	3	6	
94	LOWERY EXCAVATING	MACKINAW, IL	51790-40	ABOVE WATER	027FA01	A	1	2	
94	LOWERY EXCAVATION	MACKINAW, IL	51790-37	ABOVE WATER	027FA01	A	3	3	
94	MIDWEST MATERIALS	HENRY, IL	51230-16	ABOVE WATER	027FA01	B	1	2	
94	MIDWEST MATERIALS	LACON, IL	51230-09	ABOVE WATER	027FA02	B	1	2	
94	OTTER CREEK S. & G.	ENION, IL	50570-04	BELOW WATER	027FA01	B	1	2	
94	OTTER CREEK S. & G.	ENION, IL	50570-04	ABOVE & BELOW WATER	027FA01	B	2	6	
94	OZINGA MATERIALS	HENRY, IL	51230-27	ABOVE & BELOW WATER	027FA01	B	1	1	
94	OZINGA MATERIALS	LACON, IL	51230-22	BELOW WATER	027FA02	B	1	1	
94	OZINGA MATERIALS	LACON, IL	51230-26	ABOVE WATER	027FA02	B	1	1	
94	PEORIA CONC. CONST.	SPRING BAY, IL	52030-29	BELOW WATER	020CA16	A	3	3	
94	PEORIA CONC. CONST.	SPRING BAY, IL	52030-29	BELOW WATER	027FA01	B	3	9	

* ASR Rating - Indicates ASR Expansion Value Range; A = < 0.16, B = 0.17 - 0.27, C = > 0.28; Please contact individual sources for ASR Expansion Value, when needed

** Testing Frequency: 1's, sample as needed until 3 tests are completed; 2's, sample in 2011; 3's, sample in 2010; Note: only 1 sample required per year indicated

***Where applicable, ASTM C 1293 results used; Replace ASTM C 1260 results with 0.08; Resample required during year indicated

ALKALI-SILICA POTENTIAL REACTIVITY RATING LIST **April 30, 2010**

This list supersedes the February 5, 2010 list. Note: Changes are not high-lighted on this list.

The following values are based on Illinois Modified ASTM C 1260 test results.

Please Note: Each coarse aggregate limestone or dolomite shall have an assigned expansion value of 0.05% and each fine aggregate limestone or dolomite (manufactured stone sand) shall have an assigned expansion value of 0.03%, unless otherwise noted below.

Dist.	Producer Name	Location	P/S No.	Ledge Description	Material Code	ASR Rating*	Testing** Frequency	Number of Tests	C 1293 Test***
94	PEORIA CONC. CONST.	SPRING BAY, IL	52030-29	BELOW WATER	020CA11	A	3	3	
94	PEORIA CONC. CONST.	SPRING BAY, IL	52030-29	BELOW WATER	021CA16	A	1	1	
94	PEORIA CONC. CONST.	SPRING BAY, IL	52030-29	BELOW WATER	020CA14	B	1	2	
94	POWLEY S. & G.	SPRING BAY, IL	52030-17	ABOVE & BELOW WATER	027FA01	B	3	3	
94	POWLEY S. & G.	SPRING BAY, IL	52030-17	ABOVE & BELOW WATER	020CA14	A	1	1	
94	PSCHIRRER ASPHALT CO	LIVERPOOL, IL	50570-09	BELOW WATER	027FA01	B	1	1	
94	RIVERSIDE MATERIALS	CHILLICOTHE, IL	51430-09	BELOW WATER	027FA01	B	3	3	
94	SAND HILL MATERIALS	ELLISVILLE, IL	50570-10	ABOVE & BELOW WATER	027FA01	B	3	5	
94	SPRING SAND & GRAVEL	BURLINGTON, IA	52200-01	BELOW WATER	027FA01	C	3	3	
94	TRICON	HENNEPIN, IL	51550-07	ABOVE & BELOW WATER	027FA02	B	1	1	
94	TRICON	HENNEPIN, IL	51550-07	ABOVE WATER	027FA02	A	1	2	
94	TRICON	HENNEPIN, IL	51550-07	ABOVE & BELOW WATER	027FA01	A	1	2	
94	VALLEY SAND & GRAVEL	WASHBURN, IL	51230-25	ABOVE & BELOW WATER	027FA01	A	2	3	
94	VALLEY SAND & GRAVEL	WASHBURN, IL	51230-25	BELOW WATER	027FA01	A	1	1	
94	VALLEY SAND & GRAVEL	WASHBURN, IL	51230-25	ABOVE WATER	027FA01	B	1	1	
94	VALLEY SAND & GRAVEL	WASHBURN, IL	51230-25	ABOVE WATER	020CA11	A	1	1	
95	CARRI SCHARF MATL CO	HEYWORTH, IL	51130-06	BELOW WATER	020CA16	A	2	5	

* ASR Rating - Indicates ASR Expansion Value Range; A = < 0.16, B = 0.17 - 0.27, C = > 0.28; Please contact individual sources for ASR Expansion Value, when needed

** Testing Frequency: 1's, sample as needed until 3 tests are completed; 2's, sample in 2011; 3's, sample in 2010; Note: only 1 sample required per year indicated

***Where applicable, ASTM C 1293 results used; Replace ASTM C 1260 results with 0.08; Resample required during year indicated

ALKALI-SILICA POTENTIAL REACTIVITY RATING LIST **April 30, 2010**

This list supersedes the February 5, 2010 list. Note: Changes are not high-lighted on this list.

The following values are based on Illinois Modified ASTM C 1260 test results.

Please Note: Each coarse aggregate limestone or dolomite shall have an assigned expansion value of 0.05% and each fine aggregate limestone or dolomite (manufactured stone sand) shall have an assigned expansion value of 0.03%, unless otherwise noted below.

Dist.	Producer Name	Location	P/S No.	Ledge Description	Material Code	ASR Rating*	Testing** Frequency	Number of Tests	C 1293 Test***
95	CARRI SCHARF MATL CO	HEYWORTH, IL	51130-06	BELOW WATER	027FA01	B	2	5	
95	INTERSTATE SAND & GR	WEST LEBANON, IN	52100-32	ABOVE & BELOW WATER	021CA16	B	3	3	
95	INTERSTATE SAND & GR	WEST LEBANON, IN	52100-32	ABOVE & BELOW WATER	027FA01	B	2	5	
95	MID-AMERICA AGG.	MAHOMET, IL	50190-04	BELOW WATER	027FA01	B	2	5	
95	ROBERTSON GRAVEL PIT	CLINTON, IN	52100-47	ABOVE & BELOW WATER	027FA01	B	1	2	
95	ROSKOVENSKY CONCRETE	CLINTON, IN	52100-14	ABOVE & BELOW WATER	027FA01	B	2	5	
95	ROSKOVENSKY CONCRETE	CLINTON, IN	52100-14	ABOVE & BELOW WATER	020CA11	A	2	5	
95	ROWE CONSTRUCTION CO	HEYWORTH, IL	51130-80	BELOW WATER	027FA01	B	2	5	
95	ROWE CONSTRUCTION CO	HEYWORTH, IL	51130-80	BELOW WATER	020CA16	A	2	3	
95	S & G EXCAVATING	MONTEZUMA, IN	52100-05	ABOVE & BELOW WATER	027FA01	B	2	6	
95	SAND VALLEY S.&G.	DANVILLE, IL	51830-01	ABOVE WATER	027FA01	B	2	5	
95	SHADY REST MATERIALS	MAHOMET, IL	50190-18	ABOVE & BELOW WATER	027FA01	B	2	4	
95	STARK EXCAVATING	SHIRLEY, IL	51130-84	BELOW WATER	027FA01	B	2	5	
95	STARK EXCAVATING	SHIRLEY, IL	51130-85	BELOW WATER	027FA01	B	1	2	
95	STARK MATERIALS, INC	MAHOMET, IL	50190-17	ABOVE & BELOW WATER	027FA01	A	2	5	
95	WABASH VALLEY GRAV.	WILLIAMSPORT, IN	52100-36	ABOVE WATER	027FA01	B	1	1	
96	BUCKHART SAND & GRAV	BUCKHART, IL	51670-01	BELOW WATER	020CA16	A	3	4	

* **ASR Rating** - Indicates ASR Expansion Value Range; A = < 0.16, B = 0.17 - 0.27, C = > 0.28; Please contact individual sources for ASR Expansion Value, when needed

** **Testing Frequency:** 1's, sample as needed until 3 tests are completed; 2's, sample in 2011; 3's, sample in 2010; Note: only 1 sample required per year indicated

***Where applicable, ASTM C 1293 results used; Replace ASTM C 1260 results with 0.08; Resample required during year indicated

ALKALI-SILICA POTENTIAL REACTIVITY RATING LIST
April 30, 2010

This list supersedes the February 5, 2010 list. Note: Changes are not high-lighted on this list.

The following values are based on Illinois Modified ASTM C 1260 test results.

Please Note: Each coarse aggregate limestone or dolomite shall have an assigned expansion value of 0.05% and each fine aggregate limestone or dolomite (manufactured stone sand) shall have an assigned expansion value of 0.03%, unless otherwise noted below.

Dist.	Producer Name	Location	P/S No.	Ledge Description	Material Code	ASR Rating*	Testing** Frequency	Number of Tests	C 1293 Test***
96	BUCKHART SAND & GRAV	BUCKHART, IL	51670-01	BELOW WATER	027FA01	B	3	5	
96	CENTRAL STONE	TAYLOR, MO	52300-39	BELOW WATER	020CA16	B	1	1	
96	CENTRAL STONE	TAYLOR, MO	52300-39	BELOW WATER	027FA01	B	3	3	
96	IDEAL SAND CO.	WAYLAND, MO	52300-21	BELOW WATER	027FA01	C	3	3	
96	SANGAMON VALLEY S&G	SPRINGFIELD, IL	51670-03	BELOW WATER	027FA01	B	1	2	
96	SANG-CHRIS S&G	BUCKHART, IL	51670-26	BELOW WATER	027FA01	A	3	4	
96	SHIPLEY CONTRACTING	FORT MADISON, IA	52200-42	ABOVE & BELOW WATER	027FA01	C	1	2	
96	SMITH, WAYNE	LOUISIANA, MO	52300-20	MISSISSIPPI RIVER SAND	027FA01	C	3	3	
96	VULCAN MATERIAL CO.	ROCHESTER, IL	51670-23	BELOW WATER	027FA01	B	3	8	
96	VULCAN MATERIAL CO.	ROCHESTER, IL	51670-23	BELOW WATER	020CA16	A	1	2	
97	ALLENDAL GRAVEL CO	LAWRENCEVILLE, IL	51010-04	ABOVE & BELOW WATER	027FA01	B	1	1	
97	ALLENDAL GRAVEL CO	LAWRENCEVILLE, IL	51010-06	ABOVE & BELOW WATER	027FA01	B	3	3	
97	C. & H. GRAVEL PIT	GREENUP, IL	50350-06	BELOW WATER	027FA01	A	1	1	
97	CENTRAL ILL. MATLS	VANDALIA, IL	50510-04	ABOVE & BELOW WATER	027FA01	A	3	3	
97	CHARLES HEUERMAN TRK	GREENUP, IL	50350-07	BELOW WATER	027FA01	B	2	3	
97	COUNTY MATERIALS	CHARLESTON, IL	50290-06	ABOVE WATER	027FA01	A	3	3	
97	GREGORY GRAVEL CO.	LAWRENCEVILLE, IL	51010-08	ABOVE & BELOW WATER	027FA01	B	1	1	

* ASR Rating - Indicates ASR Expansion Value Range; A = < 0.16, B = 0.17 - 0.27, C = > 0.28; Please contact individual sources for ASR Expansion Value, when needed

** Testing Frequency: 1's, sample as needed until 3 tests are completed; 2's, sample in 2011; 3's, sample in 2010; Note: only 1 sample required per year indicated

***Where applicable, ASTM C 1293 results used; Replace ASTM C 1260 results with 0.08; Resample required during year indicated

ALKALI-SILICA POTENTIAL REACTIVITY RATING LIST **April 30, 2010**

This list supersedes the February 5, 2010 list. Note: Changes are not high-lighted on this list.

The following values are based on Illinois Modified ASTM C 1260 test results.

Please Note: Each coarse aggregate limestone or dolomite shall have an assigned expansion value of 0.05% and each fine aggregate limestone or dolomite (manufactured stone sand) shall have an assigned expansion value of 0.03%, unless otherwise noted below.

Dist.	Producer Name	Location	P/S No.	Ledge Description	Material Code	ASR Rating*	Testing** Frequency	Number of Tests	C 1293 Test***
97	JONES & SONS, INC.	VINCENNES, IN	52100-75	ABOVE & BELOW WATER	027FA01	B	2	4	
97	KNOX COUNTY SAND	VINCENNES, IN	52100-11	ABOVE & BELOW WATER	027FA01	B	3	3	
97	LAWRENCE GRAVEL	DARWIN, IL	50230-04	BELOW WATER	020CA16	A	1	2	
97	LAWRENCE GRAVEL	DARWIN, IL	50230-04	BELOW WATER	027FA01	B	1	1	
97	LAWRENCE GRAVEL	PALESTINE, IL	50330-03	ABOVE & BELOW WATER	027FA01	B	3	5	
97	LAWRENCE GRAVEL	PALESTINE, IL	50330-03	ABOVE & BELOW WATER	020CA16	A	2	3	
97	MATTOON SAND & GRAV.	AETNA, IL	50290-04	BELOW WATER	027FA01	B	1	2	
97	PROSSER CONSTRUCTION	SHELBYVILLE, IL	51730-01	BELOW WATER	027FA01	A	3	3	
97	S & G EXCAVATING	TERRE HAUTE, IN	52100-19	ABOVE & BELOW WATER	027FA01	B	3	3	
97	S & G EXCAVATING	TERRE HAUTE, IN	52100-19	ABOVE & BELOW WATER	020CA16	A	1	2	
97	VANDALIA S. & G.	VANDALIA, IL	50510-06	ABOVE & BELOW WATER	027FA01	A	3	3	
97	VULCAN MATERIALS	HARRISTOWN, IL	51150-01	BELOW WATER	027FA01	B	3	3	
98	ALTHOFF-WEBER SAND	CAHOKIA, IL	51630-08	MISSISSIPPI RIVER SAND	027FA01	C	2	3	
98	BLUFF CITY MINERAL	ALTON, IL	51190-03	MISSISSIPPI RIVER SAND	027FA01	C	3	3	
98	BUSSEN QUARRIES	KOCH STATION, MO	52300-07	MISSISSIPPI RIVER SAND	027FA01	C	3	3	
98	CAPITAL SAND CO	JEFFERSON CITY, MO	52300-41	MISSOURI RIVER SAND	027FA01	C	1	2	
98	CARLYLE S&G-A, LTD	CARLYLE, IL	50270-07	ABOVE & BELOW WATER	027FA01	A	2	3	

* ASR Rating - Indicates ASR Expansion Value Range; A = < 0.16, B = 0.17 - 0.27, C = > 0.28; Please contact individual sources for ASR Expansion Value, when needed

** Testing Frequency: 1's, sample as needed until 3 tests are completed; 2's, sample in 2011; 3's, sample in 2010; Note: only 1 sample required per year indicated

***Where applicable, ASTM C 1293 results used; Replace ASTM C 1260 results with 0.08; Resample required during year indicated

ALKALI-SILICA POTENTIAL REACTIVITY RATING LIST **April 30, 2010**

This list supersedes the February 5, 2010 list. Note: Changes are not high-lighted on this list.

The following values are based on Illinois Modified ASTM C 1260 test results.

Please Note: Each coarse aggregate limestone or dolomite shall have an assigned expansion value of 0.05% and each fine aggregate limestone or dolomite (manufactured stone sand) shall have an assigned expansion value of 0.03%, unless otherwise noted below.

Dist.	Producer Name	Location	P/S No.	Ledge Description	Material Code	ASR Rating*	Testing** Frequency	Number of Tests	C 1293 Test***
98	CENTRAL STONE	FLORISSANT, MO	52300-38	MISSOURI RIVER SAND	027FA01	C	3	4	
98	COLUMBIA QUARRY CO.	DUPO, IL	51632-09	4.3M ABOVE LEDGE 1A & 2	022CA11	A	1	1	
98	COLUMBIA QUARRY CO.	DUPO, IL	51632-09	4.3M ABOVE LEDGE 1A & 2	022CA05	A	1	1	
98	GATEWAY S&G, LTD	MADISON, IL	51190-10	BELOW WATER	027FA01	C	3	7	
98	GRANITE CITY SLAG	GRANITE CITY, IL	51193-31	ACBF SLAG	023CM11	A	1	1	
98	IRON MT. TRAP ROCK	IRON MOUNTAIN, MO	52302-33	22.9M L1-W. PIT	022CA07	B	1	1	
98	KEYESPORT S. & G. #2	KEYESPORT, IL	50050-06	BELOW WATER	027FA01	B	1	2	
98	KEYESPORT S. & G. #2	KEYESPORT, IL	50050-06	ABOVE & BELOW WATER	027FA01	B	2	3	
98	KIMATERIALS, INC.	OLD MONROE, MO	52300-33	BELOW WATER	027FA01	C	1	2	
98	LAFARGE A & C	ST. CHARLES, MO	52300-23	MISSOURI RIVER SAND	027FA01	C	2	3	
98	LEAD BELT MATERIAL	ELVINS, MO	52302-45	21.3M LEDGE 1	022CA11	A	1	1	
98	MARTIN MARIETTA	PRAIRIE DU ROCHER, I	51572-05	8.5M LEDGE 1	022CA16	A	1	1	
98	METRO EAST SAND	E. ST. LOUIS, IL	51630-06	BELOW WATER	027FA01	C	3	3	
98	QUALITY SAND CO.	COLLINSVILLE, IL	51190-08	BELOW WATER	027FA01	C	3	3	
98	RUTGER STREET SAND	ST. LOUIS, MO	52300-16	BELOW WATER	027FA01	C	3	4	
98	SIMPSON MATERIALS	VALLEY PARK, MO	52300-14	BELOW WATER	027FA01	A	3	4	
98	SIMPSON MATERIALS	VALLEY PARK, MO	52300-14	ABOVE & BELOW WATER	027FA01	A	1	1	

* **ASR Rating** - Indicates ASR Expansion Value Range; A = < 0.16, B = 0.17 - 0.27, C = > 0.28; Please contact individual sources for ASR Expansion Value, when needed

** **Testing Frequency**: 1's, sample as needed until 3 tests are completed; 2's, sample in 2011; 3's, sample in 2010; Note: only 1 sample required per year indicated

***Where applicable, ASTM C 1293 results used; Replace ASTM C 1260 results with 0.08; Resample required during year indicated

ALKALI-SILICA POTENTIAL REACTIVITY RATING LIST
April 30, 2010

This list supersedes the February 5, 2010 list. Note: Changes are not high-lighted on this list.

The following values are based on Illinois Modified ASTM C 1260 test results.

Please Note: Each coarse aggregate limestone or dolomite shall have an assigned expansion value of 0.05% and each fine aggregate limestone or dolomite (manufactured stone sand) shall have an assigned expansion value of 0.03%, unless otherwise noted below.

Dist.	Producer Name	Location	P/S No.	Ledge Description	Material Code	ASR Rating*	Testing** Frequency	Number of Tests	C 1293 Test***
98	WEBER, FRED, INC.	CRYSTAL CITY, MO	52300-37	MISSISSIPPI RIVER SAND	027FA01	C	3	4	
98	WINTER BROS. CO. #2	ST. LOUIS, MO	52300-43	BELOW WATER	027FA01	A	1	1	
98	WINTER BROS. CO. #2	ST. LOUIS, MO	52300-43	ABOVE & BELOW WATER	027FA01	A	3	3	
99	BRENDA KAY CONST.	BENTON, MO	52300-40	BELOW WATER	027FA01	C	3	5	
99	DELTA MATERIALS CO.	METROPOLIS, IL	51270-14	OHIO RIVER SAND	027FA01	B	3	5	
99	IMI-SOUTH, LLC	HENDERSON, KY	50590-01	BELOW WATER	027FA01	B	2	5	
99	J & B S&G, LLC	MAUNIE, IL	51930-07	ABOVE & BELOW WATER	027FA01	B	1	1	
99	J & B S&G, LLC	MAUNIE, IL	51930-07	BELOW WATER	027FA01	B	3	4	
99	MULZER CR. STONE CO.	EVANSVILLE, IN	52100-49	BELOW WATER	027FA01	B	3	3	
99	MULZER CR. STONE CO.	GRIFFIN, IN	52100-22	ABOVE & BELOW WATER	027FA01	B	1	2	
99	MULZER CR. STONE CO.	GRIFFIN, IN	52100-22	BELOW WATER	027FA01	B	3	4	
99	SHAWNEE S & G	GRIMSBY WYE, IL	50770-02	BELOW WATER	027FA01	C	2	4	

* ASR Rating - Indicates ASR Expansion Value Range; A = < 0.16, B = 0.17 - 0.27, C = > 0.28; Please contact individual sources for ASR Expansion Value, when needed

** Testing Frequency: 1's, sample as needed until 3 tests are completed; 2's, sample in 2011; 3's, sample in 2010; Note: only 1 sample required per year indicated

***Where applicable, ASTM C 1293 results used; Replace ASTM C 1260 results with 0.08; Resample required during year indicated